

# Rotuba CA MH

Cellulose Acetate

Rotuba Extruders, Inc.

## Message:

Rotuba CA MH is a cellulose acetate (CA) product. It can be processed by injection molding and is available in North America. Rotuba CA MH's application areas include tools, consumer goods and medical/health care. The main features are: environmental protection/green.

| General Information         |                      |                   |             |
|-----------------------------|----------------------|-------------------|-------------|
| Features                    | Updatable resources  |                   |             |
|                             | Good stability       |                   |             |
|                             | Good color stability |                   |             |
| Uses                        | Mould                |                   |             |
|                             | Buttons              |                   |             |
|                             | Toys                 |                   |             |
|                             | Glasses              |                   |             |
| Forms                       | Particle             |                   |             |
| Processing Method           | Injection molding    |                   |             |
| Physical                    | Nominal Value        | Unit              | Test Method |
| Specific Gravity            | 1.27                 | g/cm <sup>3</sup> | ASTM D792   |
| Water Absorption (24 hr)    | 2.3                  | %                 | ASTM D570   |
| Hardness                    | Nominal Value        | Unit              | Test Method |
| Rockwell Hardness (R-Scale) | 66                   |                   | ASTM D785   |
| Mechanical                  | Nominal Value        | Unit              | Test Method |
| Tensile Strength            |                      |                   | ASTM D638   |
| Yield                       | 26.2                 | MPa               | ASTM D638   |
| Fracture                    | 36.2                 | MPa               | ASTM D638   |
| Tensile Elongation (Yield)  | 43                   | %                 | ASTM D638   |
| Flexural Modulus            | 1100                 | MPa               | ASTM D790   |
| Flexural Strength (Yield)   | 38.6                 | MPa               | ASTM D790   |
| Impact                      | Nominal Value        | Unit              | Test Method |
| Notched Izod Impact         |                      |                   | ASTM D256   |
| -40°C                       | 64                   | J/m               | ASTM D256   |
| 23°C                        | 230                  | J/m               | ASTM D256   |
| Injection                   | Nominal Value        | Unit              |             |
| Drying Temperature          | 66 - 77              | °C                |             |
| Drying Time                 | 2.0 - 4.0            | hr                |             |
| Rear Temperature            | 193 - 204            | °C                |             |
| Middle Temperature          | 193 - 204            | °C                |             |

|                    |              |     |
|--------------------|--------------|-----|
| Front Temperature  | 193 - 204    | °C  |
| Nozzle Temperature | 199 - 210    | °C  |
| Mold Temperature   | 43 - 54      | °C  |
| Injection Pressure | 7.58 - 9.65  | MPa |
| Back Pressure      | 0.00 - 0.345 | MPa |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT