

MAXTEL® 600T18

Compounded Polypropylene

MRC Polymers, Inc.

Message:

For automotive exterior applications. Excellent process ability and dimensional stability. Further information and details are available upon request.

General Information			
Filler / Reinforcement	Talc,18% Filler by Weight		
Features	Good Dimensional Stability		
	Good Processability		
Uses	Automotive Exterior Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	59		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	15.0	MPa	ISO 527-2
Flexural Modulus	1150	MPa	ISO 178
Flexural Stress	22.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	28	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed, 3.20 mm)	70.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT