

Spartech Polycom PP5120 D92

Polypropylene Homopolymer

Spartech Polycom

Message:

20% Talc Filled Homopolymer Polypropylene compound offers a high level of stiffness and heat deflection performance balanced with excellent processability. This product is available in black colors. A Spartech Polycom representative can provide further information on this and other Spartech Polycom products.

General Information			
Filler / Reinforcement	Talc filler, 20% filler by weight		
Features	Rigid, good		
	Homopolymer		
	Workability, good		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	33.1	MPa	ASTM D638
--	33.1	MPa	ASTM D638
Flexural Modulus - Secant	1900	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	32	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	116	°C	ASTM D648
1.8 MPa, not annealed	60.0	°C	ASTM D648
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	47		ASTM D523

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

