## TRILOY® TP220T

Polycarbonate + ABS

Samyang Corporation

## Message:

TRILOY® TP220T is a Polycarbonate + ABS (PC+ABS) product. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/2.16			
kg)	16	g/10 min	ASTM D1238
Water Absorption (23°C, 24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	49.0	МРа	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	4710	МРа	ASTM D790
Flexural Strength (Yield)	83.4	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	29	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8			
MPa, Unannealed)	80.0	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

