

# Generic Alkyd - Mineral

Alkyd

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Alkyd - Mineral  
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.09 to 2.15	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (23°C)	0.30 to 0.45	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050 to 0.30	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Barcol Hardness	60 to 65		ASTM D2583
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength (Yield, 23°C)	82.7 to 105	MPa	ASTM D790
Compressive Strength (23°C)	124 to 159	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	77 to 160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	232 to 260	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C)	12 to 13	kV/mm	ASTM D149
Dielectric Constant (23°C)	5.98 to 7.30		ASTM D150
Dissipation Factor (23°C)	0.010 to 0.070		ASTM D150
Arc Resistance	180 to 186	sec	ASTM D495

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT