

Nycal™ 1850R13

Polyamide 6
Technical Polymers, LLC

Message:

Nycal™ 1850R13 is a Polyamide 6 (Nylon 6) material filled with 13% glass fiber. It is available in North America for injection molding. Primary attribute of Nycal™ 1850R13: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	113	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2
Flexural Modulus (23°C)	4800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	7.0	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	195	°C	ISO 75-2/B
1.8 MPa, Unannealed	170	°C	ISO 75-2/A
Peak Melting Temperature	220	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0 to 80.0	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	65.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

