

TITANPRO® SM488

Polypropylene Random Copolymer

Lotte Chemical Titan (M) Sdn. Bhd.

Message:

TITANPRO® SM488 is a Polypropylene Random Copolymer (PP Random Copolymer) material. It is available in Asia Pacific for injection molding or injection stretch blow molding.

Important attributes of TITANPRO® SM488 are:

- Clarity
- Copolymer
- Food Contact Acceptable
- Good Aesthetics
- Impact Resistant
- Typical applications include:
 - Food Contact Applications
 - Containers
 - Bottles
 - Household Applications
 - Medical/Healthcare

General Information			
UL YellowCard		E166760-100447975	
Features	Food Contact Acceptable		
	Good Impact Resistance		
	Good Surface Finish		
	High Clarity		
	High Rigidity		
	Random Copolymer		
Uses	Bottles		
	Containers		
	Household Goods		
	Medical/Healthcare Applications		
	Thin-walled Containers		
Agency Ratings	FDA 21 CFR 177.1520(a) 3 (i)		
	FDA 21 CFR 177.1520(b)		
	FDA 21 CFR 177.1520(c) 3.1a		
Processing Method	Injection Molding		
	Injection Stretch Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238

Molding Shrinkage - Flow	1.3 to 1.4	%	
Water Absorption (24 hr)	0.020	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	92		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	28.4	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus	1180	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	76.0	°C	ASTM D648
Additional Information	Nominal Value		
CAS Number	9010-79-1		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

