

AIE PA66 60G6F

Polyamide 66

Asia International Enterprise (Hong Kong) Limited

Message:

AIE PA66 60G6F is a polyamide 66 (nylon 66) material, which contains a filler of 30% glass fabric reinforcement. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. The processing method is injection molding.

The main features of AIE PA66 60G6F are:

flame retardant/rated flame

Flame Retardant

Hard

Good dimensional stability

General Information			
UL YellowCard	E252275-619186		
Filler / Reinforcement	Glass fabric reinforcement, 30% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Flame retardancy		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage	0.30 - 0.60	%	Internal method
Water Absorption (23°C, 24 hr)	1.6	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	160	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	8100	MPa	ISO 178
Flexural Stress	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	16	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	260	°C	ISO 75-2/B
1.8 MPa, not annealed	250	°C	ISO 75-2/A
Melting Temperature (DSC)	265	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 2		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Glow Wire Ignition Temperature (1.60 mm)	960	°C	IEC 60695-2-13

Injection	Nominal Value	Unit
Drying Temperature	80.0 - 100	°C
Drying Time	4.0 - 6.0	hr
Rear Temperature	250 - 280	°C
Middle Temperature	240 - 270	°C
Front Temperature	240 - 260	°C
Nozzle Temperature	250 - 280	°C
Mold Temperature	50.0 - 110	°C
Injection Pressure	30.0 - 80.0	MPa
Holding Pressure	40.0 - 50.0	MPa
Back Pressure	5.00 - 10.0	MPa
Injection instructions		

Cylinder Temperature 4: 240 to 260°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

