

# RTP 207 Z

Polyamide 66

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'  
The data for this material has not been recently verified.  
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 40% filler by weight		
Agency Ratings	FDA not rated		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12400	MPa	ASTM D638
Tensile Strength	193	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	11000	MPa	ASTM D790
Flexural Strength	290	MPa	ASTM D790
Compressive Strength	145	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	120	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1100	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	254	°C	ASTM D648
1.8 MPa, not annealed	243	°C	ASTM D648
CLTE - Flow	3.4E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.52	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257

Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.80		ASTM D150
Dissipation Factor (1 MHz)	0.015		ASTM D150
Arc Resistance	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94

#### Additional Information

The value listed as Flammability, UL 94, was tested in accordance with RTP test standards. Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 5mil/in. Tensile Elongation, ASTM D-638: 2-4%

Injection	Nominal Value	Unit
Drying Temperature	79.4	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Suggested Max Regrind	20	%
Rear Temperature	274 - 288	°C
Middle Temperature	274 - 288	°C
Front Temperature	274 - 288	°C
Mold Temperature	65.6 - 107	°C
Injection Pressure	82.7 - 138	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

