

Laser+® W 4000 (K42A)

Polyethylene Terephthalate

DAK Americas LLC

Message:

Laser+® W 4000 (K42A) is a Polyethylene Terephthalate (PET) material. It is available in Latin America or North America for injection blow molding or stretch blow molding.

Important attributes of Laser+® W 4000 (K42A) are:

- Copolymer
- Eco-Friendly/Green
- Food Contact Acceptable
- High ESCR (Stress Crack Resistant)
- Medium Viscosity

Typical applications include:

- Bottles
- Food Contact Applications

General Information	
Features	Copolymer Food Contact Acceptable High ESCR (Stress Crack Resist.) Medium-low Viscosity Recyclable Material
Uses	Bottles
Agency Ratings	FDA FCN 635
Forms	Pellets
Processing Method	Injection Blow Molding Stretch Blow Molding

Physical	Nominal Value	Unit	Test Method
Bulk Density	833	kg/m ³	Internal Method
Acetaldehyde	< 2.0	ppm	Internal Method
Color			Internal Method
CIE b*	-5.9 to -3.1		
CIE L*	> 69		
Crystallinity	> 35	%	Internal Method
Intrinsic Viscosity	0.73 to 0.77	dl/g	Internal Method
Moisture Content - as packaged	< 0.25	wt%	Internal Method
Particle Size - Shape (Spherical)	3.40	mm	Internal Method
Chip Size - nominal	31.0	count/g	Internal Method
Fines - as packaged, +24 Mesh Size	< 0.1	wt%	Internal Method
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	244	°C	Internal Method

Injection	Nominal Value	Unit
Drying Temperature	149 to 166	°C
Drying Time	4.0 to 6.0	hr
Dew Point	< -36.7	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

