

Mecoline S RDX 1212 F

Thermoplastic
Melos GmbH

Message:
Halogen-free, low smoke, flexible at low temperatures, highly oil and extra fuel resistant, radiation cross-linkable, flame retardant, max. operating temperature 125°C, compound for power and telecommunication cables for offshore/Shipboard applications.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Fuel Resistant		
	Good Flexibility		
	Halogen Free		
	High Heat Resistance		
	Irradiation Crosslinkable		
	Low Smoke Emission		
	Low Temperature Flexibility		
Uses	Oil Resistant		
	Cable Jacketing		
	Power Cable Jacketing		
	Telecommunications		
	Wire & Cable Applications		
Agency Ratings	IEC 60092-359 SHF2		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (165°C/21.6 kg)	19	g/10 min	ISO 1133
Mooney Viscosity (ML 1+4, 160°C)	26	MU	DIN 53523
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	87		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			IEC 811-1-1
-- ¹	11.1	MPa	
-- ²	4.40	MPa	
Tensile Strain			
Break ³	270	%	IEC 811-1-1

Break ⁴	400	%	IEC 811-1-1
Break, -40°C	110	%	ISO 527-2
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air			IEC 811-1-2
120°C, 240 hr	22	%	
150°C, 168 hr	18	%	
Change in Tensile Strain at Break in Air			IEC 811-1-2
120°C, 240 hr	-0.50	%	
150°C, 168 hr	-21	%	
Thermal	Nominal Value	Unit	Test Method
Hot Set ⁵			IEC 540
Elongation under load	15	%	
Residual elongation	5.0	%	
Head Temperature	165 to 185	°C	
Extruder Screw L/D Ratio	20.0:1.0 to 25.0:1.0		
Extruder Screw Compression Ratio	1.0:1.2		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	28	%	ASTM D2863
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	110 to 130	°C	
Cylinder Zone 2 Temp.	120 to 140	°C	
Cylinder Zone 3 Temp.	130 to 150	°C	
Cylinder Zone 4 Temp.	140 to 160	°C	
Cylinder Zone 5 Temp.	150 to 170	°C	
Adapter Temperature	155 to 175	°C	
Die Temperature	170 to 190	°C	
NOTE			
1.	After crosslinking		
2.	Before crosslinking		
3.	After crosslinking		
4.	Before crosslinking		
5.	at 200°C/15min/0.2 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT