

Hostacom PPU X9057HS C11354

Polypropylene Copolymer
LyondellBasell Industries

Message:

Hostacom PPU X9057HS is an unfilled PP copolymer, with medium flowability, high rigidity and good impact resistance. This product is also available in other colors, new colors can be developed depending on customer requirements. For regulatory compliance information, see Hostacom PPU X9057HS C11354 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). This grade is not intended for medical, pharmaceutical, food and drinking water applications.

General Information			
Features	Low VOC		
	Low density		
	Rigidity, high		
	Rigid, good		
	Copolymer		
	Impact resistance, good		
	Good UV resistance		
	Good liquidity		
	Good color stability		
	Good wear resistance		
	Medium liquidity		
	Scratch resistance		
	The smell is low to none		
	Excellent appearance		
Uses	Application in Automobile Field		
	Car interior parts		
Appearance	Available colors		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.910	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	11	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus ¹ (23°C)	1400	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
0°C	5.0	kJ/m ²	ISO 179/1eA
23°C	8.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
---	------	----	------------

NOTE

1. 1.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

