

Celcon® M270™

Acetal (POM) Copolymer

Celanese Corporation

Message:

Celcon® acetal copolymer grade M270™ is a lower molecular weight, high - flow grade designed for superior moldability in multi-cavity, intricate or hard to fill molds applications.

Chemical abbreviation according to ISO 1043-1: POM

Please also see Hostaform® C 27021.

General Information			
UL YellowCard	E38860-239310		
Features	Low molecular weight		
	Fast molding cycle		
	Good formability		
	High liquidity		
	General		
Uses	General		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	23.0	cm ³ /10min	ISO 1133
Molding Shrinkage			
Flow	2.2	%	ASTM D955
Transverse flow	1.8	%	ASTM D955
Vertical flow direction	1.6	%	ISO 294-4
Flow direction	1.7	%	ISO 294-4
Water Absorption			
Saturated, 23°C	0.75	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield, 23°C	60.7	MPa	ASTM D638
Yield	67.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	8.0	%	ISO 527-2/1A/50
Tensile Creep Modulus			
ISO 899-1			

1 hr	2300	MPa	ISO 899-1
1000 hr	1300	MPa	ISO 899-1
Flexural Modulus (23°C)	2750	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.2	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	110	kJ/m ²	ISO 179/1eU
23°C	120	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	5.4	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	156	°C	ISO 75-2/B
1.8 MPa, not annealed	110	°C	ASTM D648
1.8 MPa, not annealed	103	°C	ISO 75-2/A
Melting Temperature ¹	166	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.1E-4	cm/cm/°C	ISO 11359-2
Lateral	1.2E-4	cm/cm/°C	ISO 11359-2
Fill Analysis	Nominal Value	Unit	Test Method
Density of Melt	1.200	g/cm ³	Internal method
Ejection Temperature	165	°C	Internal method
Specific Heat Capacity of Melt	2210	J/kg/°C	Internal method
Thermal Conductivity of Melt	0.16	W/m/K	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 100	°C	
Drying Time	3.0	hr	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	180 - 190	°C	
Nozzle Temperature	190 - 200	°C	
Processing (Melt) Temp	180 - 200	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow-Moderate		
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 0.500	MPa	
Injection instructions			
Manifold Temperature: 180 to 200°C Zone 4 Temperature: 190 to 200°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

