

Hostacom TRC 352NA

Polyolefin
LyondellBasell Industries

Message:

Hostacom TRC 352NA high melt flow, high flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has excellent impact/stiffness balance, good flowability properties, and excellent scratch resistance. It has an outstanding blooming resistance at elevated temperatures. It was designed primarily for interior automotive applications.

General Information			
Additive	Impact Modifier		
Features	Good Impact Resistance		
	High Flow		
	High Stiffness		
	Impact Modified		
	Scratch Resistant		
Uses	Automotive Interior Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	20.0	MPa	ISO 527-2/50
Flexural Modulus ¹ (23°C)	1850	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.5	kJ/m ²	
23°C	35	kJ/m ²	
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT