

OXPEKK® MG300

Polyetherketoneketone

Oxford Performance Materials, Inc.

Message:

OXPEKK® MG300 is a Polyetherketoneketone (PEKK) material. It is available in Europe or North America for extrusion. Primary attribute of OXPEKK® MG300: Crystalline.

Typical application of OXPEKK® MG300: Medical/Healthcare

General Information			
Features	Crystalline		
Uses	Medical/Healthcare Applications		
Forms	Preformed Parts		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (400°C/8.4 kg)	20 to 30	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.4	%	ASTM D955
Water Absorption (24 hr)	< 0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	88		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4410	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	138	MPa	
Break	110	MPa	
Tensile Elongation			ASTM D638
Yield	4.5	%	
Break	> 30	%	
Flexural Modulus	4550	MPa	ASTM D790
Flexural Strength (5.0% Strain)	193	MPa	ASTM D790
Compressive Strength	207	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	175	°C	ASTM D648
Glass Transition Temperature	163	°C	DSC
Melting Temperature	360	°C	DSC
CLTE - Flow	2.1E-5	cm/cm/°C	ASTM D696

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

