

STYRON™ 685DL

General Purpose Polystyrene

Americas Styrenics LLC

Message:

STYRON™685DL is a general-purpose polystyrene material. This product is available in North America or Latin America and is processed by extrusion or injection molding.

STYRON™The main features of 685DL are:

high strength

accessible food

Heat resistance

Typical application areas include:

Foam

food contact applications

medical/health care

General Information			
Features	High tensile strength		
	Heat resistance, high		
	Compliance of Food Exposure		
Uses	Foam		
	Medical devices		
Agency Ratings	FDA 21 CFR 177.1640		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	1.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 - 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (L-Scale)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3170	MPa	ASTM D638
Tensile Strength (Break)	52.0	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	3240	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Tensile Rupture	52.0	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	21	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	98.0	°C	ASTM D648
1.8 MPa, not annealed	89.0	°C	ASTM D648
Vicat Softening Temperature	108	°C	ASTM D1525
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Rear Temperature	200 - 215	°C	
Middle Temperature	215 - 230	°C	
Front Temperature	230 - 245	°C	
Nozzle Temperature	230 - 245	°C	
Back Pressure	0.200 - 1.50	MPa	
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	177 - 193	°C	
Cylinder Zone 2 Temp.	182 - 204	°C	
Cylinder Zone 3 Temp.	188 - 210	°C	
Cylinder Zone 4 Temp.	199 - 216	°C	
Cylinder Zone 5 Temp.	204 - 221	°C	
Adapter Temperature	193 - 232	°C	
Melt Temperature	193 - 232	°C	
Die Temperature	199 - 232	°C	
Extrusion instructions			

Polish Rolls: 66 - 104 °C Head Pressure: 10 - 21 MPA

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

