

TOTAL Polyethylene Lumicene® M 1811 PCE

Linear Low Density Polyethylene

TOTAL Refining & Chemicals

Message:

Lumicene® mPE M1811 PCE is a metallocene based Linear Low Density Polyethylene with hexene as comonomer. This product contains slip and anti-block agents.

Lumicene® mPE M1811 PCE can be processed at high output rates with low extrusion pressure, excellent bubble stability and gauge control in comparison with conventional LLDPE and other metallocene based polyethylene.

Lumicene® mPE M1811 PCE is especially dedicated to film applications where excellent optical properties in combination with outstanding impact resistance (even at low temperature) and sealing strength are required, particularly in blend and coextrusion with LLDPE or LDPE.

Lumicene® mPE M1811 PCE is suited for many applications in the field of consumer, industrial, food or hygiene packaging such as bags, deep freeze, stretch hood and lamination.

General Information			
Additive	Processing aid		
	Anti-caking agent		
	Antioxidation		
	slip agent		
Features	Ultra-high impact resistance		
	Low density		
	smoothness		
	Optical		
	Anti-caking property		
	Antioxidation		
	Low temperature impact resistance		
Uses	Packaging		
	Films		
	Bags		
Processing Method	Blow film		
Physical	Nominal Value	Unit	Test Method
Density	0.919	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ISO 1133
Films	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-3
MD: Yield	10.0	MPa	ISO 527-3
TD: Yield	10.0	MPa	ISO 527-3
MD: Fracture	68.0	MPa	ISO 527-3
TD: Fracture	62.0	MPa	ISO 527-3
Tensile Elongation			ISO 527-3

MD: Fracture	670	%	ISO 527-3
TD: Fracture	700	%	ISO 527-3
Dart Drop Impact	> 1200	g	ISO 7765-1
Elmendorf Tear Strength			ISO 6383-2
MD : 1000 μm	110	N	ISO 6383-2
TD : 1000 μm	170	N	ISO 6383-2
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	105	°C	ISO 306
Melting Temperature	111	°C	ISO 11357-3
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	75		ASTM D2457
Haze	5.5	%	ISO 14782
Extrusion	Nominal Value	Unit	
Melt Temperature	180 - 230	°C	
Extrusion instructions			

BUR: 1.5:1 to 4.5:1 Die Gap: 0.8 to 2.8 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

