# Pinnacle PP 6180C3

### Polypropylene Random Copolymer

**Pinnacle Polymers** 

#### Message:

80 MELT FLOW CLARIFIED RANDOM COPOLYMER FOR INJECTION MOLDING Pinnacle Polymers Polypropylene 6180C3 is made via UNIPOL<sup>™</sup> PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency. This product is intended for injection molding applications that require high melt flow, more stiffness, faster cycle time, low bloom, enhanced processability and excellent clarity. This product contains a new generation clarifier. The 6180C3 product provides: Low bloom High melt flow, excellent processability New generation clarifier Increased stiffness Reduced cycle-time Improved color

Increased stiffness

General Information			
Additive	Clarifier		
Features	Fast Molding Cycle		
	Good Processability		
	High Clarity		
	High Flow		
	Low Blooming		
	Random Copolymer		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16			
kg)	80	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield, 3.20 mm,			
Injection Molded)	28.3	МРа	ASTM D638
Tensile Elongation <sup>2</sup> (Yield, 3.20 mm, Injection Molded)	14	%	ASTM D638
Flexural Modulus - 1% Secant <sup>3</sup> (3.20 mm,			
Injection Molded)	1100	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact <sup>4</sup> (23°C, 3.20 mm, Injection Molded)	48	J/m	ASTM D256
Notched Izod Impact (Area) <sup>5</sup> (23°C, 3.20 mm, Injection Molded)	4.70	kJ/m²	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45	79.0	۰C	
MPa, Unannealed)	78.0	L	ASTIM D648
Optical	Nominal Value	Unit	
Haze (1270 µm)	9.0	%	
Yellowness Index	< -10	YI	
NOTE			
1.	Type I, 51 mm/min		
2.	Type I, 51 mm/min		
3.	Type I, 1.3 mm/min		
4.	Туре І		
5.	Туре І		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

