

# Yuyao PP TL202 (GF)

Polypropylene

Yuyao Tenglong Plastics Co., Ltd.

## Message:

Yuyao PP TL202 (GF) is a Polypropylene product filled with 20% glass fiber. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PP TL202 (GF) include housings, agricultural, appliances and industrial applications. Characteristics include:  
Flame Rated  
Corrosion Resistant  
Heat Resistant

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Corrosion Resistance		
	Good Flow		
	Good Strength		
	High Heat Resistance		
Uses	Appliance Components		
	Electrical Housing		
	Housings		
	Industrial Applications		
	Irrigation Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	70.0	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	4000	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	8.00	kJ/m <sup>2</sup>	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	150	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		

Injection	Nominal Value	Unit
Drying Temperature	90.0 to 95.0	°C
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	215 to 245	°C
Mold Temperature	45.0 to 80.0	°C
Injection Pressure	70.0 to 90.0	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

