

ULTEM™ ATX200 resin

Polyether Imide + PCE

SABIC Innovative Plastics

Message:

High flow Polyetherimide blend. RoHS compliant, UL94 V0 Listing.

General Information			
UL YellowCard	E45329-100397331		
Features	High liquidity		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	24	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (340°C/5.0 kg)	16.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow ¹	0.50 - 0.70	%	Internal method
Flow: 3.20mm	0.50 - 0.70	%	Internal method
Transverse flow: 3.20mm	0.50 - 0.70	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.90	%	ISO 62
Equilibrium, 23°C, 50% RH	0.50	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	125	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	3300	MPa	ASTM D638
--	3000	MPa	ISO 527-2/1
Tensile Strength			
Yield ³	97.0	MPa	ASTM D638
Yield	95.0	MPa	ISO 527-2/50
Fracture ⁴	85.0	MPa	ASTM D638
Fracture	75.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁵	7.0	%	ASTM D638
Yield	6.5	%	ISO 527-2/50
Fracture ⁶	70	%	ASTM D638
Fracture	20	%	ISO 527-2/50
Flexural Modulus			

50.0mm span ⁷	3170	MPa	ASTM D790
-- ⁸	3100	MPa	ISO 178
Flexural Stress			
--	125	MPa	ISO 178
Yield, 50.0mm span ⁹	145	MPa	ASTM D790
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	20.0	mg	Internal method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹⁰			ISO 179/1eA
-30°C	4.0	kJ/m ²	ISO 179/1eA
23°C	4.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	55	J/m	ASTM D256
23°C	53	J/m	ASTM D256
-30°C ¹¹	5.0	kJ/m ²	ISO 180/1A
23°C ¹²	5.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	2100	J/m	ASTM D4812
Reverse Notch Izod Impact (3.20 mm)	2700	J/m	ASTM D256
Instrumented Dart Impact (23°C, Total Energy)	50.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, unannealed, 100 mm span ¹³	195	°C	ISO 75-2/Be
1.8 MPa, unannealed, 3.20mm	187	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	191	°C	ASTM D648
1.8 MPa, unannealed, 100 mm span ¹⁴	180	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	209	°C	ASTM D1525 ¹⁵
--	210	°C	ISO 306/A50
--	200	°C	ISO 306/B50
--	205	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -40 to 150°C	5.0E-5	cm/cm/°C	ASTM E831
Flow: 23 to 150°C	5.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 150°C	5.0E-5	cm/cm/°C	ASTM E831
Horizontal: 23 to 150°C	5.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.23	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250
50 Hz	2.90		IEC 60250

60 Hz	2.90		IEC 60250
1 MHz	2.90		IEC 60250
Dissipation Factor			IEC 60250
50 Hz	1.0E-3		IEC 60250
60 Hz	1.0E-3		IEC 60250
1 MHz	5.0E-3		IEC 60250
Comparative Tracking Index	150	V	IEC 60112
High Amp Arc Ignition (HAI)	PLC 4		UL 746
Hot-wire Ignition (HWI)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-2		UL 94
1.50 mm	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	130 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Hopper Temperature	80.0 - 100	°C	
Rear Temperature	320 - 340	°C	
Middle Temperature	330 - 350	°C	
Front Temperature	340 - 360	°C	
Nozzle Temperature	340 - 360	°C	
Processing (Melt) Temp	340 - 380	°C	
Mold Temperature	125 - 140	°C	
NOTE			
1.	Tensile Bar		
2.	5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	Type 1, 5.0 mm/min		
5.	Type 1, 5.0 mm/min		
6.	Type 1, 5.0 mm/min		
7.	1.3 mm/min		
8.	2.0 mm/min		
9.	1.3 mm/min		
10.	80*10*4 sp=62mm		
11.	80*10*4		
12.	80*10*4		
13.	120*10*4 mm		
14.	120*10*4 mm		
15.	标准 B (120°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT