TRIMID® N6-G13L

Polyamide 6

Polymer Technology and Services, LLC

Message:

TRIMID® N6-G13L is a Polyamide 6 (Nylon 6) product filled with 13% glass fiber. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Primary characteristic: lubricated.

Filler / Reinforcement Additive Features Forms	Glass Fiber,13% Filler by Weight Lubricant Lubricated Pellets Injection Molding Nominal Value		
Features Forms	Lubricated Pellets Injection Molding		
Forms	Pellets Injection Molding		
	Injection Molding		
D ' M.II I	· · ·		
Processing Method	Nominal Value		
Physical	Nominal value	Unit	Test Method
Specific Gravity	1.21	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.50	%	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	110	МРа	ASTM D638
Tensile Elongation (Break)	8.0	%	ASTM D638
Flexural Modulus	3450	МРа	ASTM D790
Flexural Strength (Yield)	152	МРа	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.17 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	232	°C	ASTM D648
Melting Temperature	255	°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	< 216	°C	
Middle Temperature	227 to 254	°C	
Front Temperature	238 to 266	°C	
Nozzle Temperature	238 to 266	°C	
Processing (Melt) Temp	232 to 271	°C	
Mold Temperature	21.1 to 93.3	°C	
Injection Pressure	82.7 to 172	MPa	
Back Pressure	0.00 to 0.345	MPa	
Screw Speed	40 to 80	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

