APICAL 500NP

PI Film

Kaneka North America LLC

Message:

APICAL 500NP is a PI Film material. It is available in Latin America or North America.

| General Information | | | |
|---|---------------|---------|------------------|
| Forms | Film | | |
| Physical | Nominal Value | Unit | Test Method |
| Water Absorption (23°C, 24 hr) | < 3.0 | % | IPC TM-650 2.6.2 |
| Films | Nominal Value | Unit | Test Method |
| Tensile Strength | | | ASTM D882A |
| MD : Break | > 228 | MPa | |
| TD : Break | > 228 | MPa | |
| Tensile Elongation | | | ASTM D882A |
| MD : Break | > 50 | % | |
| TD : Break | > 50 | % | |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity (200°C) | > 1.0E+12 | ohms·cm | ASTM D257 |
| Dielectric Strength ¹ (in Air) | > 120 | kV/mm | ASTM D149 |
| Dielectric Constant (1 kHz) | < 3.90 | | ASTM D150 |
| Dissipation Factor (1 kHz) | < 3.5E-3 | | ASTM D150 |
| NOTE | | | |
| 1. | 500 V/sec | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

