

# tefabloc® TP SD 310 30A

Thermoplastic Elastomer

Mitsubishi Chemical Performance Polymers, Inc.

Message:

tefabloc®TP SD 310 30A is a thermoplastic elastomer (TPE) material. This product is available in North America or Europe. The processing method is injection molding.

tefabloc®The main features of TP SD 310 30A are:

- ROHS certification
- chemical resistance
- high liquidity
- accessible food
- Good UV resistance

Typical application areas include:

- outdoor applications
- Sealing applications
- Consumer goods
- Sporting goods

General Information			
Features	Good UV resistance		
	High liquidity		
	Good chemical resistance		
	alkali resistance		
	acid resistance		
	Detergent resistance		
	Compliance of Food Exposure		
	Excellent appearance		
Uses	Seals		
	Outdoor application		
	Sporting goods		
	Toys		
Agency Ratings	EN 71-3		
	EU 2000/53/EC		
RoHS Compliance	RoHS compliance		
Appearance	Opacity		
Forms	Particles		
Processing Method	Injection molding		
Resin ID (ISO 1043)	>PP		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm <sup>3</sup>	ISO 1183

Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	37	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec, Injection Molded)	30		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
20% strain	0.500	MPa	ISO 37
100% strain	1.00	MPa	ISO 37
Tensile Stress (Break)	2.70	MPa	ISO 37
Tensile Elongation (Break)	790	%	ISO 37
Tear Strength <sup>1</sup>	14	kN/m	ISO 34-1
Compression Set <sup>2</sup> (23°C, 72 hr)	24	%	ISO 815
Aging	Nominal Value	Unit	
Resistance to Aging	125	°C	
Service Temperature	-50 - 70	°C	
Injection	Nominal Value	Unit	
Rear Temperature	160	°C	
Middle Temperature	170	°C	
Front Temperature	180	°C	
Injection Rate	Moderate		
Screw Compression Ratio	2.5:1.0 - 3.0:1.0		
Injection instructions			
Screw Speed: Medium			
NOTE			
1.	Method B, right-angle specimen (without cut)		
2.	Type B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT