

Tectron H2456

Thermoplastic Vulcanizate

TECTRON Systems Pte Ltd

Message:

Economical Grade

A thermoplastic vulcanizate with excellent heat and low temperature resistance. It can withstand temperature ranging from -50°C to 135°C. Tectron H series are available in concentrate and compound with hardness ranging from 45A - 90A. The concentrate is designed for compounders to obtain TPVs with the addition of PP and other chemicals. It can also be used as an additive to enhance the overall properties of various polymers. It can be processed by conventional plastics machines i.e. injection molding and extrusion.

General Information			
Features	Good wear resistance		
	Heat resistance, high		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.01	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	60		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	0.920	MPa	ASTM D412
Tensile Strength (Yield)	4.26	MPa	ASTM D412
Tensile Elongation (Break)	920	%	ASTM D412
Compression Set			ASTM D395
25°C, 22 hr	26	%	ASTM D395
100°C, 22 hr	96	%	ASTM D395
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	110 - 120	°C	
Middle Temperature	120 - 130	°C	
Front Temperature	130 - 140	°C	
Nozzle Temperature	140 - 150	°C	
Mold Temperature	30.0 - 40.0	°C	
Back Pressure	0.00 - 0.0800	MPa	
Screw Speed	35 - 110	rpm	
Injection instructions			
Injection Speed: 20 to 80 mm/s1st Stage - Boost Pressure: 1350 to 6000Hold Time (thick part): 2 to 15 sec			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

