Eleme NGL010FY

Linear Low Density Polyethylene Eleme Petrochemical Company Ltd

Message:

NGL010FY is a Butene Co-monomer based Liner Low Density Polyethylene Resin manufactured by IEPL using "SCLAIRTECH" solution polymerisation process of DU Pont, Canada (Now Nova Chemicals) offers narrow molecular weight distribution copolymer with medium slip & antiblock additive which has been specifically designed for the production of high strength blown film of various thickness for multilayer & heavy duty bags.

General Information				
Additive	Anti-caking agent			
	Moderate caking resistance			
	Moderate smoothness			
	Moderate smoothness			
Features	Low speed solidification crystal point			
	Butene comonomer			
	High strength			
	Perforation resistance			
	Anti-caking property			
	Good tear strength			
	Narrow molecular weight distribution			
	Moderate caking resistance			
	Moderate smoothness			
Uses	Blown Film			
	Packaging			
	Films			
	Bags			
	Industrial application			
	Mixing			
	Heavy packing bag			
Appearance	Natural color			
Processing Method	Blow film			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.919	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/2.16	1.0	40	ACTI 4 7 4000	
kg)	1.0	g/10 min	ASTM D1238	
Films	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D882	
MD: Yield	12.5	MPa	ASTM D882	

TD: Yield	12.0	MPa	ASTM D882
MD: Fracture	38.0	MPa	ASTM D882
TD: Fracture	30.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	650	%	ASTM D882
TD: Fracture	800	%	ASTM D882
Additional Information	Nominal Value	Unit	Test Method
Dart Impact	34.3	kN/m	ASTM D1709
Tear Strength			ASTM D1922
MD	32.4	kN/m	ASTM D1922
TD	101.0	kN/m	ASTM D1922

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

