

BONDYRAM® TL3125

Polyethylene

Polyram Ram-On Industries

Message:

Modified Polyethylene.

General Information			
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.923	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.5	g/10 min	ASTM D1238, ISO 1133
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	128	°C	ISO 11357-3, ASTM D3417

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

