

Electrafil® J-1/CF/10

Polyamide 66

Techmer Engineered Solutions

Message:

Electrafil® J-1/CF/10 is a polyamide 66 (nylon 66) product, which contains a 10% carbon fiber reinforced material. It can be processed by injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Electrafil® The application fields of J-1/CF/10 include packaging, engineering/industrial accessories, automobile industry, commercial/office supplies and conveyor belts.

Features include:

flame retardant/rated flame

ROHS certification

Conductivity

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 10% filler by weight		
Features	Conductivity		
	Antistatic property		
Uses	Packaging		
	Bushing		
	Conveyor accessories		
	Automotive Electronics		
	Business equipment		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.30	%	ASTM D955
Water Absorption (24 hr)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	7580	MPa	ASTM D638
Tensile Strength (23°C)	138	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	4.0	%	ASTM D638
Flexural Modulus (23°C)	6890	MPa	ASTM D790
Flexural Strength (23°C)	207	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	43	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	430	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, not annealed	260	°C	ASTM D648
1.8 MPa, not annealed	249	°C	ASTM D648
CLTE - Flow	2.7E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.5E+4	ohms	ASTM D257
Volume Resistivity	5.5E+2	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94

Additional Information

Surface Resistivity, ASTM D4496: 1E4-1E5 ohmsVolume Resistivity, ASTM C611: 1E2-1E3 ohm-cm

Injection	Nominal Value	Unit
Drying Temperature	82.2	°C
Drying Time	2.0 - 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	282 - 293	°C
Middle Temperature	288 - 299	°C
Front Temperature	277 - 288	°C
Nozzle Temperature	271 - 304	°C
Processing (Melt) Temp	282 - 304	°C
Mold Temperature	79.4 - 104	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.00 - 0.345	MPa

Injection instructions

Screw Speed: SlowRecommendations for Molding and Tool Conditions: Well vented moldMoisture Content, as received: Product is packaged at 0.2% or less.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT