

Hyundai EP TOP COAT PT900W / 2101

Polypropylene

HYUNDAI EP Co., Ltd.

Message:

Hyundai EP TOP COAT PT900W / 2101 is a Polypropylene product. It is available in Asia Pacific. Typical application: Coating Applications.

General Information			
Uses	Coating Applications		
	Pipe Coatings		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.880 to 0.920	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.70 to 1.1	g/10 min	ASTM D1238
Water Absorption (24 hr)	< 0.010	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	> 80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	> 23.5	MPa	ASTM D638
Tensile Elongation (Break)	500	%	ASTM D638
Flexural Modulus	> 78.5	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	> 145	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT