

Nylex™ 2185

Polyamide + PP
Multibase, A Dow Corning Company

Message:

Nylex™ 2185 is a Polyamide + PP (Nylon+PP) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Characteristics include:
Good Adhesion
Impact Resistant

General Information			
Features	Bondability		
	Good Colorability		
	Good Impact Resistance		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.974	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.1	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	38.6	MPa	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Flexural Modulus	1630	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Gardner Impact	28.2	J	ASTM D5420
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	193	°C	
Middle Temperature	204	°C	
Front Temperature	221	°C	
Nozzle Temperature	232	°C	
Processing (Melt) Temp	232	°C	
Mold Temperature	26.7 to 48.9	°C	
Injection Rate	Moderate-Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

