

EPDM 774P

Hydrocarbon Rubber

The Dow Chemical Company

Message:

EPDM 774P is a high molecular weight semi-crystalline grade and offers fast cure rates and high states of cure with standard sulfur cure systems. It offers high green strength and high extensibility. It is designed for extruded applications such as profiles and hoses. It is also suitable for molded goods.

Main Characteristics:

- Semi-crystalline
- Medium diene
- High molecular weight
- High green strength

Applications:

- Hoses
- Extruded profiles/weather strip
- Plastics modification

Notes:

Can be used in contact with all foods except water in oil emulsions, high or low fat, and low moisture fats and oil.

Adhesives only

Complies with

- U.S. FDA 21 CFR 177.2600
- U.S. FDA 21 CFR 177.1520
- U.S. FDA 21 CFR 175.105
- U.S. FDA 21 CFR 177.1210

Consult the regulations for complete details.

General Information			
Agency Ratings	FDA 21 CFR 175.105		
	FDA 21 CFR 175.1520		
	FDA 21 CFR 177.1210		
	FDA 21 CFR 177.2600		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.870	g/cm ³	ASTM D297
Mooney Viscosity (ML 1+4, 125°C)	65 - 75	MU	ASTM D1646
Ethylene Content	68.0 - 72.0	wt%	ASTM D3900
Ethylidene Norbornene (ENB) Content	4.5 - 5.3	wt%	ASTM D6047
Propylene content	25.0	wt%	ASTM D3900
Residual conversion metal		ppm	Internal method
Molecular Weight Distribution	Medium		Internal method
Ash Content		wt%	ASTM D5667
Volatile Matter		wt%	Internal method
Additional Information			

Storage and Handling:The quality of EPDM products may be affected by exposure to artificial or natural light. This product should be stored indoors in its original packaging and out of direct sunlight.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

