

Kaneka MUH LG5053

Acrylonitrile Butadiene Styrene

Kaneka Corporation

Message:

Kaneka MUH LG5053 is an acrylonitrile butadiene styrene (ABS) material. This product is available in North America and is processed by injection molding. The main features of Kaneka MUH LG5053 are:

- low gloss
- Good processability
- Impact resistance
- Heat resistance

Typical application areas include:

- Electrical/electronic applications
- Automotive Industry

General Information			
Features	Gloss, low		
	Impact resistance, good		
	Good formability		
	Heat resistance, high		
Uses	Electrical/Electronic Applications		
	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50 - 0.80	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	44.0	MPa	ASTM D638
Tensile Elongation (Break)	30	%	ASTM D638
Flexural Modulus	2300	MPa	ASTM D790
Flexural Strength	72.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	50	J/m	ASTM D256
-30°C, 6.40 mm	50	J/m	ASTM D256
23°C, 3.20 mm	90	J/m	ASTM D256
23°C, 6.40 mm	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648

0.45 MPa, not annealed	120	°C	ASTM D648
1.8 MPa, not annealed	110	°C	ASTM D648
CLTE - Flow	8.0E-5	cm/cm/°C	ASTM D696
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	20		ASTM D523
Additional Information			

Coefficient of Linear Thermal Expansion, Kaneka Method, flow: 7-9 E-5 cm/cm/°C Mold Shrinkage, Kaneka Method, flow, 73°F: 5-8 mil/in Spiral Flow, Kaneka Method, 482°F: 17.3 in Reflective Rate, Kaneka Method, 60°, 73°F: 20 %

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

