

# Daelim Po1y® XP5300

Metallocene Linear Low Density Polyethylene

DAELIM INDUSTRIAL CO., LTD.

Message:

Daelim Po1y®XP5300 is a metallocene linear low density polyethylene product. It is available in Europe or Asia Pacific. Daelim Po1y®The application areas of XP5300 include film, agriculture, food contact applications and coating applications.

Features include:  
Good sealing performance  
Antiblock software  
high gloss  
high strength  
slide

General Information			
Additive	Processing aid		
	Anti-caking agent		
	Antioxidation		
	slip agent		
Features	Low extract		
	Low temperature heat sealability		
	Rigid, good		
	Highlight		
	High strength		
	smoothness		
	Anti-caking property		
	Antioxidation		
	Good heat sealability		
	Definition, high		
	Good toughness		
Uses	Films		
	Laminate		
	Agricultural application		
Agency Ratings	FDA 21 CFR 177.1520		
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD: Broken, 30 μm, blown film	53.9	MPa	ASTM D882
TD: Broken, 30 μm, blown film	42.2	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 30 μm, blown film	610	%	ASTM D882

TD: Broken, 30 µm, blown film	650	%	ASTM D882
Dart Drop Impact (30 µm, Blown Film)	300	g	ASTM D1709A
Seal Initiation Temperature <sup>1</sup> (30 µm, Blown Film)	93.0	°C	Internal method
Elastomers	Nominal Value	Unit	Test Method
Tear Strength			ASTM D1004
Lateral flow: 0.0300mm	113	kN/m	ASTM D1004
Traffic: 0.0300mm	108	kN/m	ASTM D1004
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 30.0 µm, Blown Film)	89		ASTM D2457
Haze (30.0 µm, Blown Film)	15	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	150 - 170	°C	
NOTE			
1.	HGT, 2.8 kg, 0.5 sec		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

