

# RJM SN601G40-F

Polyamide 66

RJM International, Inc.

## Message:

RJM SN601G40-F is a Polyamide 66 (Nylon 66) product filled with 40% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Additive/Masterbatch. Primary characteristic: flame rated.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Uses	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	137	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	8830	MPa	ASTM D790
Flexural Strength	270	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	170	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	220	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	260 to 290	°C	
Mold Temperature	100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT