

Yuyao PA 055ZR16

Polyamide 66/6 Copolymer

Yuyao Tenglong Plastics Co., Ltd.

Message:

Yuyao PA 055ZR16 is a Polyamide 66/6 Copolymer (Nylon 66/6) product. It can be processed by injection molding and is available in Asia Pacific. Applications of Yuyao PA 055ZR16 include electrical/electronic applications, appliances, automotive, furniture and industrial applications. Characteristics include:
Impact Resistant
Impact Modified

General Information			
Additive	Impact Modifier		
Features	High Impact Resistance		
	Impact Modified		
	Low Temperature Impact Resistance		
Uses	Appliance Components		
	Automotive Applications		
	Camera Applications		
	Furniture		
	Industrial Applications		
	Power/Other Tools		
	Sporting Goods		
	Switches		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.5	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	57.0	MPa	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	1750	MPa	ASTM D790
Flexural Strength	75.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area)	28.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	93.0	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	

Drying Temperature	85.0 to 90.0	°C
Drying Time	6.0 to 8.0	hr
Processing (Melt) Temp	235 to 265	°C
Mold Temperature	60.0 to 90.0	°C
Injection Pressure	60.0 to 100	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

