

Generic Nylon Copolymer - Glass Fiber

Polyamide Copolymer

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic Nylon Copolymer - Glass Fiber
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Glass Fiber		
Mechanical	Nominal Value	Unit	Test Method
Flexural Stress (23°C)	170 to 236	MPa	ISO 178
Electrical	Nominal Value	Unit	Test Method
Dissipation Factor (23°C)	5.0E-3 to 0.018		IEC 60250
Comparative Tracking Index	375 to 600	V	IEC 60112

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT