

ALCOM® AWL 15/1 WT1471-04LB

Acrylonitrile Butadiene Styrene

ALBIS PLASTIC GmbH

Message:

ALCOM® AWL 15/1 WT1471-04LB is an Acrylonitrile Butadiene Styrene (ABS) product filled with 15% filler. It can be processed by injection molding and is available in Asia Pacific, Europe, or North America. Applications of ALCOM® AWL 15/1 WT1471-04LB include automotive and lighting applications. Characteristics include:

- Flame Rated
- REACH Compliant
- RoHS Compliant

General Information			
Filler / Reinforcement	Filler,15% Filler by Weight		
Features	High Reflectivity		
Uses	Automotive Applications		
	Lighting Applications		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	7.00	cm³/10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	110	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	50.0	MPa	
Break	35.0	MPa	
Tensile Strain			ISO 527-2
Yield	2.8	%	
Break	12	%	
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	9.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	93.0	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	HB		
3.00 mm	HB		
Additional Information	Nominal Value	Unit	Test Method
Tristimulus Value			
Y10 of Reflection	94	%	DIN 5033
Y10 of Transmittance : 500.0 μm	0.50	%	ISO 13468
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	220 to 260	°C	
Mold Temperature	50.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT