Manner Flexible PVC V970 NAT601

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

Message:

Recommended Applications: 105°C Insulation and Jacket Compound designed for use in CL2R, CL3R applications. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

| General Information | | | |
|--|----------------------------|-------|-------------|
| Uses | Cable Jacketing | | |
| | Insulation | | |
| | Wire & Cable Applications | | |
| | | | |
| Appearance | Natural Color | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 1.36 to 1.40 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore C, 15 sec) | 67 to 73 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ | 19.0 | MPa | ASTM D638 |
| Tensile Elongation ² (Break) | 350 | % | ASTM D638 |
| Aging | Nominal Value | Unit | Test Method |
| Change in Tensile Strength in Air ³ (136°C, 168 hr) | -1.0 | % | UL 1581 |
| Change in Ultimate Elongation in Air ⁴ (136°C, 168 hr) | 2.0 | % | UL 1581 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index | 34 | % | ASTM D2863 |
| NOTE | | | |
| 1. | Unaged Dumbbells: .03 inch | | |
| 2. | Unaged Dumbbells: .03 inch | | |
| 3. | Air Aged Retention | | |
| 4. | Air Aged Retention | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533 Email: sales@su-jiao.com No. 215, Lianhe North Road, Fengxian District, Shanghai, China

