Hostacom EKC 330N E1 G42824

Polyolefin

LyondellBasell Industries

Message:

"Hostacom" 330N is a 16% mineral filled, impact modified grade for interior applications with excellent impact/stiffness balance, good flowability properties and good scratch resistance. It has an outstanding blooming resistance at elevated temperatures and also low odour and low carbon emissions. The grade is available in color-matched, pellet form.

| General Information | | | | | |
|------------------------|------------------------------|-------|-------------|--|--|
| Filler / Reinforcement | Mineral,16% Filler by Weight | | | | |
| Additive | Impact Modifier | | | | |
| Features | Good Flow | | | | |
| | High Impact Resistance | | | | |
| | High Stiffness | | | | |
| | Low Blooming | | | | |
| | Low to No Odor | | | | |
| | Scratch Resistant | | | | |
| | | | | | |
| Physical | Nominal Value | Unit | Test Method | | |
| Density | 1.02 | g/cm³ | ISO 1183 | | |

| Physical | Nominal Value | Unit | Test Method |
|---|---------------|----------|--------------|
| Density | 1.02 | g/cm³ | ISO 1183 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 | | | |
| kg) | 17 | g/10 min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Yield) | 21.1 | MPa | ISO 527-2/50 |
| Flexural Modulus ¹ | 1850 | MPa | ISO 178 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | | | ISO 179/1e |
| -30°C | 5.0 | kJ/m² | |
| 23°C | 45 | kJ/m² | |
| Charpy Unnotched Impact Strength (23°C) | No Break | | ISO 179/1eU |
| Thermal | Nominal Value | Unit | Test Method |
| Heat Deflection Temperature (1.8 MPa, | | | |
| Unannealed) | 56.0 | °C | ISO 75-2/A |
| Vicat Softening Temperature | 132 | °C | ISO 306/A50 |
| NOTE | | | |
| 1. | 2.0 mm/min | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

