

Innothane® IE-40A

Polyurethane Thermoset Elastomer, Polyether Based

Innovative Polymers, Inc.

Message:

IE-40A is an elastic polyether system formulated for hand-batch processing. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA, or TDI. IE-40A is ideal for color matching due to it's neutral color.

General Information			
RoHS Compliance	RoHS Compliant		
Appearance	Off-White		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
Cured	1.10	g/cm ³	
Hardener	1.10	g/cm ³	
Base Resin	1.16	g/cm ³	
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D2566
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 100		
Hardener	Mix Ratio by Weight: 95		
	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 100		
Demold Time	720 to 1200	min	
Uncured Properties	Nominal Value	Unit	Test Method
Viscosity			
25°C ¹	0.63	Pa · s	
25°C ²	0.95	Pa · s	
25°C ³	1.7	Pa · s	
Curing Time ⁴	40	hr	
Gel Time	20 to 30	min	
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	32 to 42		ASTM D2240
Tensile Strength	3.48	MPa	ASTM D638
Tensile Elongation at Break	400	%	ASTM D638
Tear Strength	13.1	kN/m	ASTM D624
NOTE			

1.	Resin
2.	Mixed
3.	Hardener
4.	24 hours at 77°F + 16 hours at 150°F

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

