

BP RPP 2009 GK BLK

Polypropylene

Buckeye Polymers, Inc.

Message:

Our Glass Reinforced product lines exhibit increased Tensile Strength, stiffness, and Heat Deflection. Highly optimized Glass Reinforced PP resins have successfully replaced engineering thermoplastics in numerous applications.

Features:

Good Flexural Strength

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Good Stiffness		
	Good Strength		
Uses	Engineered Applications		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0 to 12	g/10 min	ASTM D1238
Carbon Black Content	1.0	%	ASTM D1603
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	> 1490	MPa	ASTM D790
Additional Information	Nominal Value	Unit	
Glass Fiber Content	16 to 22	%	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

