

Celstran® +PP-GF30-05CN01/10

Polypropylene
Celanese Corporation

Message:

Material code according to ISO 1043-1: PP
Polypropylene with 30 weight percent ash content, long glass fibers reinforced. Impact modified, copolymer. The fibers are chemically coupled to the polypropylene matrix. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long.
Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.
The very isotropic shrinkage in the molded parts minimizes the warpage.
Complex parts can be manufactured with high reproducibility by injection molding.
Application field: Functional/structural parts for automotive

General Information			
Filler / Reinforcement	Long glass fiber, 30% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
	Low warpage		
	Rigidity, high		
	High strength		
	Copolymer		
	Chemical coupling		
	Impact resistance, good		
	Good creep resistance		
	Low temperature impact resistance		
Uses	Application in Automobile Field		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PP		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
--	6000	MPa	ISO 527-2/1A/1
80°C	4100	MPa	ISO 527-2/1A
Tensile Stress			

Fracture	95.0	MPa	ISO 527-2/1A/5
80°C	50.0	MPa	ISO 527-2/1A
Tensile Strain			
Fracture	2.4	%	ISO 527-2/1A/5
Fracture, 80°C	3.3	%	ISO 527-2/1A
Flexural Modulus			
23°C	6000	MPa	ISO 178
80°C	4000	MPa	ISO 178
Flexural Stress			
23°C	150	MPa	ISO 178
80°C	70.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	24	kJ/m ²	ISO 179/1eA
23°C	25	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	70	kJ/m ²	ISO 179/1eU
23°C	60	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, not annealed	156	°C	ISO 75-2/A
8.0 MPa, not annealed	124	°C	ISO 75-2/C
Melting Temperature ¹	166	°C	ISO 11357-3
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	210 - 230	°C	
Middle Temperature	230 - 240	°C	
Front Temperature	240 - 250	°C	
Nozzle Temperature	240 - 250	°C	
Processing (Melt) Temp	210 - 270	°C	
Mold Temperature	30.0 - 70.0	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow		
Holding Pressure	40.0 - 80.0	MPa	
Back Pressure	0.00 - 3.00	MPa	
Injection instructions			
Manifold Temperature: 210 to 270°CZone 4 Temperature: 250 to 250°CFeed Temperature: 20 to 50°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

