

ESPOLEX 4855

Thermoplastic Polyolefin Elastomer

Sumitomo Chemical America, Inc.

Message:

ESPOLEX 4855 is a Thermoplastic Polyolefin Elastomer (TPO (POE)) product. It can be processed by injection molding, profile extrusion, or sheet extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of ESPOLEX 4855 include hose/tubing, automotive and sheet.

General Information			
Uses	Automotive Interior Trim		
	Hose		
	Profiles		
	Sheet		
	Tubing		
Processing Method	Injection Molding		
	Profile Extrusion		
	Sheet Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	20	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	75		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	3.00	MPa	ISO 37
Tensile Stress ² (Break)	8.10	MPa	ISO 37
Tensile Elongation ³ (Break)	730	%	ISO 37
Compression Set (70°C, 22 hr)	54	%	ASTM D395
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁴			ISO 179
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature (Type A)	< -60.0	°C	ISO 812
Injection	Nominal Value	Unit	
Processing (Melt) Temp	188 to 238	°C	
NOTE			
1.	Type 1A, 500 mm/min		
2.	Type 1A, 500 mm/min		

- | | |
|----|---------------------|
| 3. | Type 1A, 500 mm/min |
| 4. | Thickness: 3.2 mm |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

