GELAST 1170

Thermoplastic Vulcanizate Guang Sung Plastics (GSPL)

Message:

GELAST 1170 is a Thermoplastic Vulcanizate (TPV) product. It can be processed by injection molding and is available in Asia Pacific. Applications of GELAST 1170 include wire & cable, electrical/electronic applications, engineering/industrial parts, hose/tubing and packaging.

Characteristics include:

RoHS Compliant

Crosslinkable

Heat Resistant

| General Information | | | |
|-------------------------------------|------------------------------------|-------|-------------|
| Features | Crosslinkable | | |
| | High Heat Resistance | | |
| | | | |
| Uses | Cable Jacketing | | |
| | Electrical/Electronic Applications | | |
| | Gaskets | | |
| | Hose | | |
| | Packaging | | |
| | Telephone Drop Wire Insulation | | |
| | | | |
| RoHS Compliance | RoHS Compliant | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Specific Gravity | 0.970 | g/cm³ | ASTM D792 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore A, 5 sec) | 73 | | ASTM D2240 |
| Elastomers | Nominal Value | Unit | Test Method |
| Tensile Set | 12 | % | ASTM D412 |
| Tensile Stress (100% Strain) | 3.33 | MPa | ASTM D412 |
| Tensile Strength (Yield) | 8.92 | MPa | ASTM D412 |
| Tensile Elongation (Break) | 520 | % | ASTM D412 |
| Thermal | Nominal Value | Unit | Test Method |
| Brittleness Temperature | -60.0 | °C | ASTM D746 |
| Additional Information | Nominal Value | Unit | Test Method |
| Tension Strength | 32.4 | kN/m | ASTM D624 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

