

Pearlbond™ 100

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Lubrizol Advanced Materials, Inc.

Message:

Pearlbond® 100 is a linear, polycaprolactone-based polyurethane, supplied in form of small white granules, which combines a very high crystallization rate with a very high thermoplasticity level. It is used for Hot Melt adhesives.

Pearlbond® 100 is mainly used for making heat-sealable fabrics (thermobonding), obtained by coating processes such as scattering or dot-coating (powder or paste). In all cases, the product is previously ground into powder, by cryogenic grinding. The particle size of the powder will depend on the application technique to be used.

General Information	
Features	Crystalline
	Good Adhesion
	Heat Sealable
Uses	Adhesives
	Coating Applications
	Fabrics
Agency Ratings	EC 1907/2006 (REACH)
Appearance	White
Forms	Granules
Processing Method	Coating
	Scatter Coating

Physical	Nominal Value	Unit	Test Method
Density (20°C)	1.19	g/cm ³	ISO 2781
Melt Mass-Flow Rate (MFR) (170°C/2.16 kg)	15 to 30	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	51		ISO 868
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	64.0 to 68.0	°C	Internal Method
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity ¹ (160°C)	700	Pa · s	ISO 1133
Additional Information	Nominal Value	Unit	Test Method
Crystallization Rate	Very High		Internal Method
Softening Range	55 to 60	°C	Internal Method
Thermoplasticity	Very High		Internal Method

NOTE

1. 2.16 Kg

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

