

Dryflex® PCW 90A331B

Thermoplastic Elastomer

ELASTO

Message:

Dryflex PCW 90A331B: Thermoplastic Elastomer

Base Material: TPO

Hardness: 90 Shore A

Service Temperature Range: -50 to +75°C (Unstressed Material).

Colour: Black

Presentation: Free flowing pellets that can be processed without predrying when stored under normal conditions

Weather Resistance: Excellent

Ozone / UV Resistance: Excellent

Chemical Resistance: Good (excluding organic solvents, aromatic and vegetable oils)

Recycling: 100% recyclable

Mould Shrinkage (linear): Approx. 0.75 - 2% depending on e.g. shape of the detail and placement of gate

Bonds to: PP, PE

General Information			
Recycled Content	Yes,33%		
Features	Good Chemical Resistance		
	Good UV Resistance		
	Good Weather Resistance		
	Ozone Resistant		
	Recyclable Material		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 2781
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	90		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	9.30	MPa	ISO 37
Tensile Stress (Yield)	9.50	MPa	ISO 37
Tensile Elongation (Break)	290	%	ISO 37
Tear Strength ¹	74	kN/m	ISO 34-1
Compression Set ² (23°C, 24 hr)	63	%	ISO 815
Injection	Nominal Value	Unit	
Rear Temperature	170 to 200	°C	
Middle Temperature	170 to 200	°C	
Front Temperature	170 to 200	°C	
Mold Temperature	15.0 to 40.0	°C	
NOTE			
1.	Method C, Crescent		
2.	Type B		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

