

Styropek® BFL 395

Expanded Polystyrene

Styropek S.A. de C.V.

Message:

Styropek® BFL products can be used in a wide variety of applications, including blocks for panels, general insulation, below grade use, fabrication, flotation, and general packaging.

Additional applications include ICF's ("insulated concrete forms"), thin or thick walled custom molding, and other general protective packaging.

Modified expandable polystyrene (EPS) / non-flammable / antifiame / auto-extinguishable containing approximately 3.45 - 3.65 wt% pentane as the blowing agent.

All products are supplied as spherical beads with a bulk density of approximately 40 lb/ft³ (640 kg/m³).

Styropek® BFL products are compatible with many anti-stat, mineral oil and color additives that can be added during processing.

Styropek® BFL products do not contain chlorofluorocarbons and hydrofluorocarbons compounds.

Intended uses

Block molding applications, especially suited for excellent surface cut appearance.

General Information		
UL YellowCard	E474710-102172942	
Additive	Foaming agent (3 to 4%) 3	
Features	Recyclable materials	
	Can foam	
	Self-extinguishing	
	Flame retardancy	
Uses	Packaging	
	Building materials	
	Architectural application field	
	Insulating material	
	Foam	
Agency Ratings	ASTM C 578	
	ASTM E 84	
	EC 1907/2006 (REACH)	
RoHS Compliance	RoHS compliance	
Forms	Sphere	
Physical	Nominal Value	Unit
Apparent Density	0.64	g/cm³
Additional Information	Nominal Value	Unit
Bead Size (600.0 to 1250.0 µm)	> 97	%
Expanded Density	15.0 - 110	kg/m³
Monomer Residue		ppm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

