

Sindustris PC GN1007FT

Polycarbonate

Sincerity Australia Pty Ltd.

Message:

Sindustris PC GN1007FT is a Polycarbonate (PC) material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris PC GN1007FT are:

Flame Rated

Flame Retardant

Halogen Free

Typical applications include:

Housings

Electrical/Electronic Applications

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Flow		
	Halogen Free		
Uses	Electrical Housing		
	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	61.8	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	> 100	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2260	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	91.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	65	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	130	°C	ASTM D648
RTI Elec	120	°C	UL 746
RTI Imp	110	°C	UL 746
RTI Str	120	°C	UL 746
Flammability	Nominal Value	Test Method	

Flame Rating			UL 94
2.00 mm	V-1		
2.50 mm	V-0		
3.00 mm	V-0		
Optical	Nominal Value	Unit	Test Method
Transmittance	89.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	105 to 115	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	240 to 260	°C	
Middle Temperature	255 to 275	°C	
Front Temperature	270 to 285	°C	
Nozzle Temperature	270 to 285	°C	
Processing (Melt) Temp	255 to 285	°C	
Mold Temperature	50.0 to 80.0	°C	
Back Pressure	0.981 to 3.92	MPa	
Screw Speed	40 to 70	rpm	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	10 mm/min		
4.	10 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

