

Makropol® PC A3 G20 NTLA010 PC305

Polycarbonate

Petropol Industry and Trade of Polymers LTDA

Message:

Polycarbonate with 20% natural fiber glass for injection molding with excellent thermal and mechanical properties.

General Information			
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>PC GF20<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35 to 1.37	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	17 to 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Water Absorption (Equilibrium)	0.16	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	105	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	5500	MPa	ASTM D790
Flexural Strength	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	145	°C	ASTM D648
Vicat Softening Temperature	160	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Dielectric Strength	19	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	6.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	90.0 to 110	°C	
NOTE			
1.	Rate A (50°C/h)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

