

KEBAFLEX® U A 85 EF B01 natural

Thermoplastic Polyurethane Elastomer

BARLOG plastics GmbH

Message:

TPU, Shore A85, natural, easy flow

General Information			
Features	Good Flow		
Appearance	Natural Color		
Resin ID (ISO 1043)	TPU		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	650	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	No Break		ISO 179/1eA

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

