

Formolene® HB5502B

High Density Polyethylene Copolymer

Formosa Plastics Corporation, U.S.A.

Message:

Formolene HB5502B is designed for applications requiring excellent stiffness and stress crack resistance properties. It may be used as a general-purpose blow molding resin or sheet extrusion thermoforming resin.

Formolene HB5502B meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

General Information			
UL YellowCard	E205741-559054		
Features	Copolymer		
	Food Contact Acceptable		
	General Purpose		
	Hexene Comonomer		
	High ESCR (Stress Crack Resist.)		
	High Stiffness		
Uses	Blow Molding Applications		
	General Purpose		
	Industrial Applications		
	Industrial Containers		
	Personal Care		
	Pharmaceutical Packaging		
	Sheet		
Agency Ratings	EC 1907/2006 (REACH)		
	FDA 21 CFR 177.1520		
Forms	Pellets		
Processing Method	Blow Molding		
	Sheet Extrusion		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Density	0.955	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.35	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance			
Compression Molded, F50	35.0	hr	ASTM D1693B
100% Igepal, Compression Molded, F50	45.0	hr	ASTM D1693A

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, Compression Molded)	27.6	MPa	ASTM D638
Tensile Elongation ² (Break, Compression Molded)	> 600	%	ASTM D638
Flexural Modulus (Compression Molded)	1380	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -118	°C	ASTM D746
NOTE			
1.	Type IV, 51 mm/min		
2.	Type IV, 51 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

